

Nazdar EC 3600 Vinyl Banner UV Screen Inks

The Economy 3600 Vinyl Banner Process Colors are UV screen inks specifically formulated for 4-color process printing of indoor and short term outdoor POP vinyl banner applications.

Substrates

Vinyl banner (PVC)

Substrate recommendations are based on commonly available materials intended for the ink's specific market when the inks are processed according to this technical data. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Reference the 'Quality Statement' at the end of this document.

Mesh

355-420 tpi (140-165 tpcm) monofilament polyester with a mesh opening of 22-40 um for most applications.

Stencil

Use direct emulsions and capillary films which are solvent resistant and UV compatible.

Squeegee

70-90 durometer polyurethane squeegee.

Coverage

Depending upon ink deposit, the estimated coverage per gallon: 3,000 – 3,600 square feet (278 - 335 square meters)

Reference www.nazdar.com/en-us/ColorStar for examples of coverage calculations.

Screen Printing

Standard items are formulated to be press ready. Thoroughly mix the ink prior to printing. Improper mixing can lead to inconsistent color and ink performance.

Maintain ink temperature at 65°-90°F (18°-32°C) for optimum print and cure performance. Lower temperatures increase the ink viscosity, impairing flow and increasing film thickness. Elevated temperatures lower the ink viscosity, reducing print definition and film thickness.

Pretest to determine optimum printing parameters for a particular set of ink, substrate, screen, press, and curing variables/conditions.

The ink can be affected by stray UV light. Be aware of skylights, windows and overhead lights curing the ink in the screen; light filters are recommended. Leaving a container uncovered may result in the ink's surface forming a "skin", caused by reaction with ambient lighting. Keep containers covered.

Nazdar does not recommend inter-mixing this ink series with other inks or series.

Cure Parameters

These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions. "Undercuring" the ink may result in poor adhesion, lower block resistance, reduced durability, and higher residual odor. "Overcuring" the ink may reduce the flexibility of the printed part and adhesion of subsequent ink layers.

Mercury Vapor UV Curing: Standard ink cures when exposed to a single medium pressure mercury vapor lamp emitting output millijoules (mJ) and milliwatts (mW) of:

80-100 mJ/cm² @ 600+ mW/cm² for most colors

To increase mJ levels, slow down the belt speed or scan speed. To increase mW levels, increase the wattage setting of the UV reactor. To optimize mJ and mW output, maintain the bulb and reflector, and ensure proper focus to the substrate. These guidelines are representative of measurements taken using an EIT® UVICURE® Plus radiometer measuring the UVA bandwidth (320-390 nm). To obtain accurate mJ readings with the UVICURE® Plus, reduce the belt speed to less than 40 ft/min.

Nazdar EC 3600 Vinyl Banner UV Screen Inks

Inter-Printable

Economy 3600 Vinyl Banner UV Process Colors do not contain Standard Printing Colors or Pantone Matching System® Base Colors. When these colors are required, use the following Nazdar Screen Ink Series to inter-print:

Nazdar 1900 UV Ink Series

Nazdar 3600 UV Ink Series

Refer to the inter-printed ink's Technical Data Sheet for processing recommendations.

Adhesion Testing

When recommended UV energy output levels are achieved, checking the degree of cure on a **cooled down** print is imperative:

- Touch of ink surface – the ink surface should be smooth.
- Thumb twist – the ink surface should not mar or smudge.
- Scratch surface – the ink surface should resist scratching.
- Cross hatch tape test – per the ASTM D-3359 method, use a cross hatch tool or a sharp knife to cut through ink film only; then apply 3M #600 clear tape on cut area, rub down, and rip off at a 180 degree angle. Ink should only come off in actual cut areas.

Full adhesion characteristics at proper cure levels are demonstrated within: 24 hours

Cleanup

For screen cleaning, similar products to those listed below may be used.

Screen Wash (Prior to Reclaim): Use IMS207 Graphic Recirculating Screen Wash or IMS203 Economy Graphic Screen Wash
Press Wash (On Press): Use IMS301 Premium Graphic Press Wash

Ink Modifications

Clears / Varnishes

Mixing Clear: use to reduce the density of colors.

Additives

The market specific performance properties of this ink series / ink item should be acceptable for most applications without the need for additives. When required, any additives should be thoroughly mixed before each use. Prior to production, test any additive adjustment to the ink. Inks containing additives should not be mixed with other inks.

Example for additives: Ink at 100g with 8% of an additive is calculated as: 100g ink + 8g additive = 108g total

Reducer / Thinner

RE306 UV Reducer to reduce the viscosity of these inks. Add up to 10%.

Gloss / Flattening Powders / Improved Slip

Use to reduce gloss and improve slip.

CARE118 UV Satin Paste at 10%, power mix into the ink.

General Information

Handling

Refer to the SDS for recommendations on handling.

Wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If product does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water.

Consult the applicable Safety Data Sheet (SDS / MSDS) for further instructions and warnings.

This ink series is a one-part, 100% solids UV-curable screen printing ink and does not contain N-vinyl-2-pyrrolidone (trade name V-Pyrol®).

For assistance on a wide range of important regulatory issues, consult the following Regulatory Compliance Department link at <http://www.nazdar.com> or contact Nazdar Ink Technologies - World Headquarters (see contact listing at the end of this document).

Nazdar EC 3600 Vinyl Banner UV Screen Inks

Weathering / Outdoor Durability

At full strength and properly cured, the outdoor durability when mounted vertically in the Central U.S.A: **6 months**

Outdoor Durability Variables

Outdoor durability cannot be specified exactly. Slight color change and loss of gloss should be expected. Variables affecting a printed part's durability include:

- Ink film thickness and degree of curing
- Color formulation: large amounts of mixing clear or white, mixing several colors into one match, and/or mixing a small quantity of any single color
- Substrate type and age
- Mounting angle and directional orientation
- Geographical location
- Degree of air pollution
- Excessive abrasion
- Non-clear coated prints exhibit more color change and loss of gloss.

Storage / Shelf Life

Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life.

Standard items supplied in 1-gallon (4/5 kilo) containers or smaller. Useable for a period of at least **24 months** from the date of manufacture.

Shelf life above applies to the standard ink items listed on this TDS. To obtain the shelf life for special inks and additives, contact Nazdar Customer Service or Nazdar Technical Service. See contact listing at the end of this document.

Halftone Colors

Halftone Extender Base is used to reduce the density of any of the halftone colors.

Standard Halftone Colors are formulated with hues and densities common to the graphic industry.

Dense Halftone Colors are formulated with increased densities over the Standard Halftone colors and are designed for printers who want to have the latitude to adjust the density levels.

Packaging / Availability

Contact your Nazdar distributor for product availability and offering.

Standard Colors

Standard ink items listed below are inventoried in gallon containers.

Item Type	Item Number	Item (or Color) Description
Halftone Colors	36EC140	Econo HT Extender Base
Halftone Colors	36EC141	Econo Halftone Cyan
Halftone Colors	36EC142	Econo Halftone Magenta
Halftone Colors	36EC143	Econo Halftone Yellow
Halftone Colors	36EC144	Econo Halftone Black
Halftone Colors	36EC151	Econo Halftone Cyan Dense
Halftone Colors	36EC152	Econo Halftone Magenta Dense
Halftone Colors	36EC153	Econo Halftone Yellow Dense
Halftone Colors	36EC154	Econo Halftone Black Dense
Halftone Colors	36EC156	Econo High Intensity HT Black
Additives	CARE118	UV Satin Paste
Additives	RE306	UV Reducer
Cleaners	IMS201	Premium Graphic Screen Wash

Nazdar EC 3600 Vinyl Banner UV Screen Inks

Cleaners	IMS203	Economy Graphic Screen Wash
Cleaners	IMS301	Premium Graphic Press Wash

Nazdar Quality Statement

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

Nazdar Ink Technologies Offices

Nazdar Ink Technologies - World Headquarters
8501 Hedge Lane Terrace
Shawnee, KS 66227-3290 USA
Toll Free US: 866-340-3579
Tel: +1 913-422-2255
Fax: +1 913-422-2296
Customer Service E-mail: NazdarOrders@nazdar.com
Technical Support E-mail: TechSupport@Nazdar.com

Nazdar Limited – EMEA
Battersea Road, Heaton Mersey
Stockport, England SK4 3EA
Tel: + 44 (0)-161-442-2111
Fax: + 44 (0)-161-442-2001
EMEA Customer Service E-mail: infoUK@nazdar.com
EMEA Technical Service E-mail: technicalservicesUK@nazdar.com

Nazdar – Asia Pacific
11 Changi North Street 1
#03-03/04
Singapore 498823
Tel: +65 6385 4611
E-mail: aspac@nazdar.com